

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 320 451 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
02.02.2005 Bulletin 2005/05

(21) Application number: **01971529.1**

(22) Date of filing: **25.09.2001**

(51) Int Cl.7: **B29C 33/00**

(86) International application number:
PCT/BE2001/000165

(87) International publication number:
WO 2002/026461 (04.04.2002 Gazette 2002/12)

(54) **METHOD AND MOULD FOR MANUFACTURING POLYURETHANE ARTICLES**

FORM UND VERFAHREN ZUM HERSTELLEN VON POLYURETHANGEGENSTÄNDEN

**PROCEDE ET MOULE POUR LA FABRICATION D'UN ARTICLE MOULE COMPRENANT AU
MOINS UNE PEAU EN POLYURETHANNE ELASTOMERE**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
RO SI

(30) Priority: **26.09.2000 EP 00870216**

(43) Date of publication of application:
25.06.2003 Bulletin 2003/26

(73) Proprietor: **RECTICEL**
1200 Brussels (BE)

(72) Inventors:

- **MALFLIET, Guy c/o Recticel**
B-9230 Wetteren (BE)
- **DE WINTER, Hugo c/o Recticel**
B-9230 Wetteren (BE)
- **WILLEMS, Jan c/o Recticel**
B-9230 Wetteren (BE)

(74) Representative: **Van Reet, Joseph**
Gevers & Vander Haeghen,
Intellectual Property House,
Brussels Airport Business Park
Holidaystraat 5
1831 Diegem (BE)

(56) References cited:
WO-A-93/23237 GB-A- 1 035 365
US-A- 4 544 518

- **PATENT ABSTRACTS OF JAPAN** vol. 004, no.
116 (M-027), 19 August 1980 (1980-08-19) & JP 55
074845 A (SUGAWA TSUNEMI), 5 June 1980
(1980-06-05) & DATABASE WPI Section Ch,
Week 18029 Derwent Publications Ltd., London,
GB; Class A26, AN 1980-50924c & JP 55 074845
A (SUGAWA T)
- **PATENT ABSTRACTS OF JAPAN** vol. 005, no.
101 (M-076), 30 June 1981 (1981-06-30) & JP 56
044633 A (HITACHI CHEM CO LTD), 23 April 1981
(1981-04-23)

*Änderungen im Vergleich zur EP 1190828
markiert*

04. FEB. 2005

EP 1 320 451 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to a method for manufacturing a moulded article, in particular an automotive vehicle's part, comprising at least an elastomeric polyurethane skin showing a front and a back, which method comprises the steps of :

- providing a mould with at least a first mould part comprising at least two mutually movable mould sections forming at least one seam;
- applying at least one reactive polyurethane mixture to a surface of said first mould part to mould said skin with its front against this mould surface;
- moving the mutually movable mould sections away from one another; and
- removing the moulded article from the mould.

[0002] In practice, mould parts consisting of mutually movable mould sections are used to increase the design freedom of the moulded articles. They allow in particular to manufacture relatively rigid or stiff moulded articles in moulds showing so-called undercuts. A drawback of the use of such moulds for moulding the skin or front surface of the moulded article is that the finishing degree of the seam between the mould sections is of utmost importance and may result in an optically not qualitative article showing traces of the seam between the mould sections.

[0003] In order to avoid this drawback, the skin can be made in a first mould and subsequently transferred to another mould wherein the further backing layers are applied. Such a method is for example disclosed in WO93/23237. When the skin is sufficiently flexible and when the opening of the first mould is sufficiently wide, the skin can be demoulded, even when the mould shows undercuts, without having to use mutually movable mould sections or so-called slides. The second mould, wherein the more rigid backing layers are applied, is then provided with the necessary movable mould sections or slides. A drawback of this known method is however that the design freedom is still somewhat limited. It allows for example not to provide a greater skin thickness in certain areas of the skin which would make the skin too stiff to demould it or to make a three dimensional skin extending in cross-section over a large angle so that the mould part shows only a relatively narrow cavity through which the skin has to be demoulded. A further disadvantage of the known method is that, in the case of undercuts, it does not enable to mould the entire article, including the backing layers, in one single mould (as illustrated for example in Figure 1 of WO93/23237) so that the skin moulded in the first mould has to be transferred to a second mould. Of course, when such a transfer step could be avoided, this would reduce the manufacturing costs, not only because less handling steps would be required but also because less skin material would be required since in areas of the article

which are cut out later to insert different inserts, no skin or backing material has to be applied.

[0004] An object of the present invention is therefore to provide a new method for manufacturing a moulded article comprising at least an elastomeric polyurethane skin which enables to provide a similar design freedom than the known moulding methods wherein moulds with mutually movable mould sections are used but which solves the problems of the traces which may be left by the seams between the movable mould sections on the visible surface of the moulded article.

[0005] To this end, the method according to the invention is characterised in that said first mould part further comprises a removable, flexible liner made of an elastic material which is positioned onto said mould sections to form at least a portion of said mould surface and to cover at least partially said seam so that, in the region or regions where the seam is covered by said liner, no trace of the seam is left on the front surface of the moulded article.

[0006] Since the seam between the mutually movable mould sections is covered by the liner, it does not leave traces on the outer surface of the moulded article. Moreover, due to the fact that the liner is flexible, it can be removed from the moulded article, even if it shows undercuts.

[0007] US-A-4 544 518 discloses to position a thin-walled stiff but flexible plate in a first mould part to cover the seams between the different mould sections of this first mould part. The plate is shaped to form a recess wherein reinforcing fibres are first introduced before positioning the plate in the mould. After having closed the mould a liquid plastics composition is injected in the mould in accordance to an injection or an injection compression moulding process. The plate is intended to increase the output rate of the mould and to prevent reinforcing fibres from penetrating between the tool parts or flash surfaces. In this way, a hermetic seal required for the injection moulding process can be achieved between the tool parts.

[0008] Providing a silicone mould showing the negative configuration of the article to be moulded in a mother mould is further already known per se from US-A-5 747 167 and US-A-5 938 993. According to US-A-5 747 167, the silicone mould was intended to reduce the tooling costs required to produce interior parts such as dash boards by injection moulding. Neither US-A-5 747 167 nor US-A-5 938 993 teaches however the use of a flexible, removable liner for covering seams between mutually movable mould parts. In fact, the mother mould carrying the silicone mould part consists of one single part. When the mould shows undercuts as illustrated in the figures of US-A-5 938 993, the moulded article cannot be demoulded unless it is a sufficiently flexible article such as for example the disclosed cushion.

[0009] In a preferred embodiment of the method according to the invention, the step of removing the moulded article from the mould comprises the step of remov-

⚡

⚡ } tech.
hier
Sarten

⚡

ing the moulded article together with the flexible liner from the mutually movable mould sections and the step of removing the flexible liner from the moulded article.

[0010] By first removing the moulded article together with the liner out of the mould, the liner can easily be removed from the moulded article. For moulding a next article, the liner can then be positioned again onto the mutually movable mould sections.

[0011] The present invention also relates to a mould for use in the method according to the invention showing at least a first mould part which forms a mould surface against which said skin is moulded and which comprises at least two mutually movable mould sections forming at least one seam. The mould of the invention is characterised in that said first mould part further comprises a removable, flexible liner made of an elastic material which is optionally grained on its side against which the skin is moulded and which is positioned onto said mould sections to form at least a portion of said mould surface and to cover at least partially said seam, the removable, flexible liner being so configured that during moulding, in the region or regions where the seam is covered by said liner, no trace of the seam is left on the front surface of the moulded article.

[0012] Further advantages and particularities of the invention will become apparent from the following description of some particular embodiments of the method and the mould according to the invention. This description is only given by way of illustrative example and is not intended to limit the scope of the invention as defined by the annexed claims. The reference numerals used in the description refer to the drawings wherein:

Figures 1 to 8 illustrate schematically the different step of a method according to the invention for manufacturing a moulded article, in particular a dashboard comprising an outer polyurethane skin layer, an intermediate foam layer and a structural backing layer; wherein

Figure 9 is similar to Figure 3 but relates to a variant embodiment of the flexible liner positioned on the mutually movable mould sections of the lower mould part; wherein

Figure 10 shows a variant embodiment of the liner illustrated in the previous figures; and wherein

Figure 11 shows a variant embodiment of the lower mould part which is only partially covered with a flexible liner.

[0013] In general, the present invention provides a new method for manufacturing moulded articles which comprise an elastomeric polyurethane skin intended to form the front side of the article. The moulded articles are for example interior trim parts of automotive vehicles such as dashboards or instrument panels, door covers, consoles and glove compartments. In addition to the polyurethane skin, they usually contain a structural backing layer or rigid carrier which may be united either

directly to the back of the skin or through the intermediary of a foam layer in order to achieve a soft touch.

[0014] In practice, the interior trim parts are often to be produced in moulds comprising slides, or in other words mutually movable mould sections, as a result of the complex shape of the trim parts and especially the presence of undercuts. When traces or imprints of the seams between the mutually movable mould sections are to be avoided on the visible side of the trim part, the skin was hitherto to be made in a separate mould comprising a relatively expensive single piece nickel or galvanic scale and was subsequently to be transferred to a second mould with mutually movable mould sections.

[0015] In the method according to the present invention, illustrated in Figures 1 to 8, visible traces or imprints of the seams between the mutually movable mould sections are however avoided without having to use a mould showing a one-piece mould surface. The lower mould part 1 illustrated in Figure 1 and used to mould the polyurethane skin and optionally the further backing layers, comprises for example three mutually movable mould sections including one basic mould section 2 and two so-called slides 3, 4. These mould sections 2 - 4 form a mould surface showing a generally concave shape and undercuts 15. In order to be able to demould the moulded article, the slides 3, 4 can be retracted to the position illustrated in Figure 5. In the closed position, the different mutually movable mould sections 2 - 4 abut each other along seams 5. Since such a mould construction is already known by the skilled person, the mechanical connection between the different mould sections 2 - 4 and the mechanism for mutually moving these sections will not be described in further detail.

[0016] An essential feature of the method according to the invention is that the mould part 1 does not only comprise the mutually movable mould sections 2 - 4 but also a removable, flexible liner 6 made of an elastic material. This liner 6 is positioned on the mould sections 2 - 4 to form at least a portion of the mould surface 7 and to cover at least partially the seams 5 between the mutually movable mould sections 2 - 4. In the example illustrated in Figure 1, the liner 6 forms the entire mould surface 7 of the lower mould part 1 and covers therefore the seams 5 completely. However, in other cases, the liner 6 could only cover a portion of the mould sections 2 - 4, the transition between the mould surface formed by the liner and the mould surface formed by the uncovered mould sections 2 - 4 being situated in an area which is either cut out afterwards or which is covered with an insert or other covering. An example of such a mould, comprising also one basic mould section 2 and two so-called slides 3, 4 is illustrated in Figure 11.

[0017] Since the flexible liner 6 forms at least a portion of the mould surface against which the article is moulded by spraying in an open mould or by injecting or pouring in a closed mould, the surface characteristics of this article, in particular the texture or grain, usually a leather texture, will be determined by the texture or grain of the

liner surface 7. The liner is preferably pre-shaped in accordance with the shape of the visible front side of the skin or the article which is to be moulded. In practice, different techniques exist for producing such a liner 6. First of all, it is possible to produce the liner by thermoforming a sheet of thermoplastic material. In such a thermoforming process, the sheet is formed against a mould surface so that it receives the desired shape and surface structure or texture. Another, more preferred way to produce the liner 6 is to mould the liner in a closed mould starting from a liquid hardenable material such as liquid silicone or a thermoplastic material. This can be done in a separate closed mould comprising a lower mould part which is substantially identical to the lower mould part 1 illustrated in Figure 1 and an upper mould part which fits in the lower mould part and which has the shape and the surface grain and texture of the article which is to be moulded. Such a technique is for example disclosed in US-A-5 747 167 and US-A-5 938 993 which are incorporated herein by way of reference. In these US patents, use is made of a master piece formed by an object desired to be reproduced to produce the silicone liners. In the method according to the present invention, the flexible liner is however preferably moulded against a nickel or more generally a galvano mould surface. The production of such galvano mould surfaces is known in practice, starting for example from a leather wrapped model, to produce mould surfaces against which skins can be moulded. For the method according to the present invention, an additional intermediate moulding step is however required to achieve a positive nickel core (against which the negative flexible liner is to be moulded) instead of a negative nickel scale.

[0018] The liner has an average thickness which will usually be situated between 0.03 mm and 15 mm and preferably between 0.05 and 5 mm. When the visual quality of the article needs not to be really outstanding, the average thickness of the flexible liner could be smaller than 0.03 mm or larger than 15 mm, for instance when another material such as leather will be glued on the front surface of the article. The average thickness of the liner is determined by measuring its volume and by dividing this volume by its area forming the mould surface. Larger thicknesses being preferred, for example a thickness of between 2 and 5 mm in view of making positioning the liner in the lower mould part 1 easier. However, as illustrated in Figure 10, one or more local projections or thickenings 8 fitting into corresponding recesses in the mutually movable mould sections 2 - 4 can also make the exact positioning of the liner in the lower mould part 1 easier.

[0019] For maintaining the liner 6 against the surface of the mould sections 2 - 4, and optionally for conforming the shape of the flexible liner 6 to the shape of the surface of these mould sections 2 - 4, the liner is preferably sucked by a vacuum applied through openings 18 distributed over the surface of the mould sections 2 - 4 against this surface.

[0020] After having positioned the flexible liner 6 in the mould, a reactive polyurethane mixture is applied to the mould surface 7 to mould the elastomeric polyurethane skin 9, as illustrated in Figure 2, with its front against this mould surface. The skin 9 has normally an average thickness in the range of 0.1 to 3 mm and usually in the range of 0.5 to 1.5 mm. In certain areas such as corners the actual skin thickness may however differ considerably from these values. Different techniques exist for moulding the polyurethane skin 9.

[0021] First of all, the reactive polyurethane mixture can be sprayed against the mould surface 7, in particular in accordance with the technique described in EP-B-0 303 305. Use can be made of a light-stable polyurethane reaction mixture as disclosed for example in EP-B-0 379 246. However, in a variant embodiment, an in-mold coating can first be applied to the mould surface, in particular a water or solvent-based paint coating. In this case, the skin material applied against the back of this coating does not necessarily have to be light-stable so that for example also aromatic polyurethane systems can be used for the skin 9.

[0022] Instead of spraying the polyurethane skin material against an open mould surface, it can also be applied by pouring or injecting, in particular in accordance with a reaction injection moulding (RIM) process, in a closed mould. In this case, a second upper mould part has of course to be provided to form the closed mould cavity. Specific reactive polyurethane mixtures which can be used for a RIM process are disclosed in WO98/14492. However, in this embodiment also, an in-mold coating or paint can first be applied to the mould surface so that the material of the skin itself does not have to be light-stable.

[0023] In the previous embodiments, the reactive polyurethane mixture did not contain blowing agents or only a small amount thereof so that a non-cellular or micro-cellular skin was obtained having a density which is usually higher than 400 kg/m³ and preferably higher than 700 kg/m³. When the skin 9 is produced in a closed mould, it is however possible to include a blowing agent in the polyurethane formulation in order to produce a polyurethane foam showing an integral elastomeric polyurethane skin.

[0024] After having moulded the skin 9, it can be removed from the mould and used to produce the moulded article, in particular the interior trim part. During this further processing, different backing layers can be applied to the elastomeric skin, for example a rigid structural backing layer which can be glued or bonded directly to the back of the skin or indirectly, through the intermediary of a foam layer, foamed between the skin and the structural backing layer. This structural backing layer may be a rigid polyurethane layer, obtained for example by an S-RIM (Structural RIM, insertion of glass fibre mat), R-RIM (Reinforced RIM, glass or other fibres admixed into the polyurethane reaction mixture) or LFI (Long Fibre Injection) or similar process, or it may be

made of a rigid thermoplastic material such as PVC, ABS and SMA.

[0025] An advantage of the method according to the present invention is however that such backing layers, which render the moulded article more rigid or stiff, can also be provided in the mould wherein the skin is moulded.

[0026] Figure 3 illustrates for example the further step wherein a structural backing layer or rigid carrier 10 is attached to an upper mould part 11 and wherein a foamable composition is poured onto the back of the skin 9 before closing the mould. The closed position of the mould is illustrated in Figure 4. In this position, the foamable composition has foamed to fill the mould cavity with a foam layer 12 and to unite the structural backing layer 10 to the back of the skin 9. Instead of pouring the foamable composition in the open mould, it could also be injected, in particular in accordance with a RIM process, in the closed mould. The foam layer is preferably made of a polyurethane material.

[0027] In a further variant embodiment, the foam layer 12 could be sprayed against the back of the skin layer 9. In a subsequent step, a reactive mixture for obtaining a structural backing layer can then be sprayed against the back of the foam layer or the mould can be closed and the reactive mixture for obtaining the structural backing layer can be injected in this closed mould, at the back side of the foam layer. Just as the foam layer, the structural backing layer is preferably made of a polyurethane material. For more details with respect to the way wherein the different backing layers can be applied in this embodiment and with respect to the composition thereof, reference is made to WO93/23237.

[0028] In still a further variant embodiment, the intermediary foam layer can optionally be omitted and the structural backing layer can be sprayed or moulded, in particular by a RIM process such as more particularly an S-RIM, an R-RIM or an LFI or similar process, directly against the back of the skin. In this embodiment, the rigid backing layer does not necessarily have to be a polyurethane material but it may also be made of a thermoplastic material injected, as disclosed in WO 00/23239, in molten state against the back of the polyurethane skin layer 9. These thermoplastic materials comprise for example polypropylene (PP), polycarbonate (PC), acrylonitrilbutadiene-styrol (ABS), ABS blends, acrylester-styrol-acrylonitril (ASA), polystyrol (PS), thermoplastic polyurethane (TPU) or mixtures thereof or mixtures of any of these components with still other thermoplastic materials.

[0029] After having moulded the skin 9 and any optional backing layers, the moulded article is demoulded. As illustrated in Figure 5, the slides 3 and 4 are first retracted according to arrows 13 and, as illustrated in Figure 6, the upper mould part 11, having the moulded article and the flexible liner attached thereto, is removed from the lower mould part. In a next step, the flexible liner 6 is drawn of the moulded part, more particularly

initially in the direction of arrows 14 shown in Figures 6 and 7. The liner 6 is made of an elastic material which has such an elasticity that it can easily be removed notwithstanding the presence of undercuts 15. Finally, the moulded article is removed from the upper mould part 11 as illustrated in Figure 8.

[0030] In a variant embodiment of the demoulding steps illustrated in Figures 5 to 8, the upper mould part 11 is first removed leaving the liner 6 and the moulded article in the lower mould part 1. Subsequently, the slides 3, 4 can be retracted and the liner 6 can be drawn aside so that the moulded article can be removed without removing the liner 6 from the basic mould section 2. An advantage of this embodiment is that the liner has not to be repositioned entirely again in the mould before moulding the next article or trim part.

[0031] In the method illustrated in the Figures, a thicker foam layer 12 was applied in the undercuts 15 so that the structural backing layer 10 could easily be inserted in the lower mould part 1. However, the structural backing layer 10 could also extend within the undercuts 15. In order to enable to insert the structural backing layer in this case in the lower mould part 1, the slides 3 and 4 can be retracted and the flexible liner or hose, having the skin moulded thereon, drawn aside over a distance sufficient to allow insertion of the structural backing layer. Once inserted, the slides and the skin and liner can be brought back to their initial position.

[0032] In order to avoid the thicker foam layer in the undercuts 15 without having to draw aside the liner and skin layer, use can also be made of an upper mould section comprising one or more slides so that this mould part can be inserted in the lower mould part. The structural backing layer can then be moulded in the mould cavity formed between the back of the skin (or optionally of the foam backing layer) and the upper mould part. Of course when spraying the structural backing layer as described hereabove, the thickness of the foam layer can also be reduced in the undercuts.

[0033] In Figure 9 a particular embodiment of the present invention is illustrated wherein, before moulding the skin layer 9, a premanufactured insert 16 is positioned on the mould surface 7 formed by the flexible liner 6. In order to avoid penetration of the skin material between the front of the insert 16 and the flexible liner 6, this liner is provided with upstanding edges 17 which abut the peripheral edge of the insert 16 when positioning it between the upstanding edges thereby forming a seal.

Claims

1. A method for manufacturing a moulded article comprising at least an elastomeric polyurethane skin (9) showing a front and a back, which method comprises the steps of :

- providing a mould with at least a first mould part (1) comprising at least two mutually movable mould sections (2-4) forming at least one seam (5);
 - applying at least one reactive polyurethane mixture to a surface (7) of said first mould part (1) to mould said skin (9) with its front against this mould surface (7);
 - moving the mutually movable mould sections (2-4) away from one another; and
 - removing the moulded article from the mould,
- characterised in that** said first mould part (1) further comprises a removable, flexible liner (6) made of an elastic material which is positioned onto said mould sections (2-4) to form at least a portion of said mould surface (7) and to cover at least partially said seam (5) so that, in the region or regions where the seam is covered by said liner, no trace of the seam is left on the front surface of the moulded article.
2. A method according to claim 1, **characterised in that** said mould surface (7) has a generally concave shape.
 3. A method according to claim 1 or 2, **characterised in that** the step of removing the moulded article from the mould comprises the step of removing the moulded article together with the flexible liner (6) from the mutually movable mould sections (2-4) and the step of removing the flexible liner (6) from the moulded article.
 4. A method according to any one of the claims 1 to 3, **characterised in that** said reactive mixture is sprayed against said first mould part (1).
 5. A method according to any one of the claims 1 to 3, **characterised in that** said mould comprises at least a second mould part (11) co-operating with the first mould part (1) to form a closed mould cavity wherein said reactive polyurethane mixture is applied in particular in accordance with a reaction injection moulding (RIM) process, said second mould part (11) being in particular composed of only one mould section.
 6. A method according to claim 5, **characterised in that** said reactive polyurethane mixture comprises a blowing agent and is formulated to produce a polyurethane foam showing said skin (9) as an integral skin moulded against said mould surface (7).
 7. A method according to any one of the claims 1 to 5, **characterised in that** said reactive polyurethane mixture is formulated to produce an elastomeric, non-cellular or micro-cellular polyurethane skin (9) having a density higher than 400 kg/m³ and prefer-

ably higher than 700 kg/m³.

8. A method according to any one of the claims 1 to 7, **characterised in that** before moving the mutually movable mould sections (2-4) away from one another to remove the moulded article from the mould, at least a first backing layer (12) is moulded against the back of the moulded skin (9).
9. A method according to claim 8, **characterised in that** the step of moulding said first backing layer (12) comprises applying a foamable composition for obtaining a foam material against the back of the moulded skin (9).
10. A method according to claim 9, **characterised in that** said foamable composition is applied between the moulded skin (9) and a second, structural backing layer (10) which is positioned on the back side of the skin (9), the foam material obtained from the foamable composition uniting the structural backing layer (10) to the back of the moulded skin (9).
11. A method according to claim 9, **characterised in that** before moving the mutually movable mould sections (2-4) away from one another to remove the moulded article from the mould, a second structural backing layer (10) is moulded against the back of the foam layer (12).
12. A method according to claim 8, **characterised in that** said first backing layer is a structural backing layer (10) made of a rigid material.
13. A method according to any one of the claims 1 to 12, **characterised in that** said flexible liner (6) is pre-shaped, in particular moulded, in accordance with the shape of the front of the skin (9).
14. A method according to claim 13, **characterised in that** said flexible liner (6) comprises a moulded silicone liner.
15. A method according to any one of the claims 1 to 14, **characterised in that** said flexible liner (6) shows, on its side against which the skin (9) is moulded, a predetermined texture and/or grain, such as a leather texture.
16. A method according to any one of the claims 1 to 15, **characterised in that** said flexible liner (6) has an average thickness of between 0.03 and 15 mm, in particular of between 0.05 and 5 mm.
17. A method according to any one of the claims 1 to 16, **characterised in that** before applying the reactive polyurethane mixture to the surface (7) of said first mould part (1) to mould said skin (9), an in-mold

coating is applied to this surface (7). in particular a water or solvent-based paint coating.

18. A method according to any one of the claims 1 to 17, **characterised in that** before applying the reactive polyurethane mixture to the surface (7) of said first mould part (1) to mould said skin (9), an insert (16) is portioned on the mould surface (7) formed by the flexible liner (6), the insert showing at least one peripheral edge by means of which it is positioned in abutment to at least one upstanding edge (17) provided on the flexible liner (6).

19. A mould for use in a method according to any one of the claims 1 to 18 and showing at least a first mould part (1) which forms a mould surface (7) against which said skin (9) is moulded with its front and which comprises at least two mutually movable mould sections (2-4) forming at least one seam (5), **characterised in that** said first mould part (1) further comprises a removable, flexible liner (6) made of an elastic material which is optionally grained on its side against which the skin (9) is moulded and which is positioned onto said mould sections (2-4) to form at least a portion of said mould surface (7) and to cover at least partially said seam (5), the removable, flexible liner being so configured that during moulding, in the region or regions where the seam is covered by said liner, no trace of the seam is left on the front surface of the moulded article.

20. A mould according to claim 19, **characterised in that** said mould surface (7) has a generally concave shape.

21. A mould according to claim 19 or 20, **characterised in that** said flexible liner (6) shows a predetermined texture and/or grain on its side against which the skin (9) is moulded and comprises in particular a moulded silicone liner.

Patentansprüche

1. Ein Verfahren zur Herstellung eines geformten Artikels, der zumindest eine Elastomer-Polyurethanhaut (9) mit einer Vorder- und einer Rückseite umfasst, wobei das Verfahren die folgenden Schritte umfasst:

- Bereitstellung eines Formstücks mit zumindest einem ersten Formteil (1), das zumindest zwei gegenseitig bewegliche Formabschnitte (2 - 4) umfasst, welche zumindest eine Naht (5) bilden;
- Auftragen zumindest einer reaktiven Polyurethanmischung auf eine Oberfläche (7) des erwähnten ersten Formteils (1), um die erwähnte

Haut (9) mit ihrer Vorderseite gegen diese Formoberfläche (7) zu formen;

- Entfernung der gegenseitig beweglichen Formabschnitte (2 - 4) weg voneinander; und
- Entnahme des geformten Artikels aus dem Formstück,

dadurch gekennzeichnet, dass das erwähnte erste Formteil (1) ferner ein herausnehmbares flexibles Futter (6) aus einem elastischen Material umfasst, das auf die erwähnten Formabschnitte (2 - 4) gelegt ist, um zumindest einen Abschnitt der erwähnten Formoberfläche (7) zu bilden und die erwähnte Naht (5) zumindest teilweise zu bedecken, sodass, in der Region oder in den Regionen, wo die Naht durch das erwähnte Futter bedeckt ist, auf der Vorderseite des geformten Artikels keine Spur der Naht sichtbar ist.

2. Ein Verfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** die erwähnte Formoberfläche (7) eine allgemein konkave Form hat.

3. Ein Verfahren nach Anspruch 1 oder 2, **dadurch gekennzeichnet, dass** der Schritt des Herausnehmens des geformten Artikels aus dem Formstück den Schritt des Herausnehmens des geformten Artikels zusammen mit dem flexiblen Futter (6) aus den gegenseitig beweglichen Formabschnitten (2 - 4) und den Schritt des Entfernens des flexiblen Futters (6) vom geformten Artikel umfasst.

4. Ein Verfahren nach einem der Ansprüche 1 bis 3, **dadurch gekennzeichnet, dass** die erwähnte reaktive Mischung gegen das erwähnte erste Formteil (1) gesprüht wird.

5. Ein Verfahren nach einem der Ansprüche 1 bis 3, **dadurch gekennzeichnet, dass** das erwähnte Formstück zumindest ein zweites Formteil (11) umfasst, das mit dem erwähnten ersten Formteil (1) kooperiert, um einen geschlossenen Formhohlraum zu bilden, in dem die erwähnte reaktive Polyurethanmischung insbesondere gemäß einem Reaktionsspritzgussverfahren (RIM) aufgebracht wird, wobei das erwähnte zweite Formteil (11) insbesondere nur aus einem Formabschnitt besteht.

6. Ein Verfahren nach Anspruch 5, **dadurch gekennzeichnet, dass** die erwähnte reaktive Polyurethanmischung ein Treibmittel umfasst und zusammengesetzt ist, um einen Polyurethanschaum zu bilden, der die erwähnte Haut (9) als integrale Haut aufweist, die gegen die erwähnte Formoberfläche (7) geformt wird.

7. Ein Verfahren nach einem der Ansprüche 1 bis 5, **dadurch gekennzeichnet, dass** die erwähnte re-

- aktive Polyurethanmischung zusammengesetzt ist, um eine elastomerische, nicht-zelluläre oder mikrozelluläre Polyurethanhaut (9) zu ergeben, die eine Dichte über 400 kg/m³ und vorzugsweise über 700 kg/m³ aufweist.
8. Ein Verfahren nach einem der Ansprüche 1 bis 7, **dadurch gekennzeichnet, dass**, bevor die gegenseitig beweglichen Formabschnitte (2 - 4) voneinander weg bewegt werden, um den geformten Artikel aus dem Formstück zu entfernen, zumindest eine erste Versteifungsschicht (12) gegen die Rückseite der geformten Haut (9) geformt wird. 5
 9. Ein Verfahren nach Anspruch 8, **dadurch gekennzeichnet, dass** der Schritt des Formens der erwähnten ersten Versteifungsschicht (12) das Auftragen einer aufschäumbaren Mischung umfasst, um ein Schaummaterial gegen die Rückseite der geformten Haut (9) zu erhalten. 10
 10. Ein Verfahren nach Anspruch 9, **dadurch gekennzeichnet, dass** die erwähnte aufschäumbare Mischung zwischen die geformte Haut (9) und eine zweite, strukturelle Versteifungsschicht (10) aufgetragen wird, welche sich auf der Rückseite der Haut (9) befindet, wobei das Schaummaterial, das aus der aufschäumbaren Mischung erhalten wurde, die strukturelle Versteifungsschicht (10) mit der Rückseite der geformten Haut (9) verbindet. 15
 11. Ein Verfahren nach Anspruch 9, **dadurch gekennzeichnet, dass**, bevor die gegenseitig beweglichen Formabschnitte (2 - 4) voneinander weg bewegt werden, um den geformten Artikel aus dem Formstück zu entfernen, eine zweite strukturelle Versteifungsschicht (10) gegen die Rückseite der Schaum- 20 schicht (12) geformt wird.
 12. Ein Verfahren nach Anspruch 8, **dadurch gekennzeichnet, dass** die erwähnte erste Versteifungsschicht eine strukturelle Versteifungsschicht (10) aus einem starren Material ist. 25
 13. Ein Verfahren nach einem der Ansprüche 1 bis 12, **dadurch gekennzeichnet, dass** das erwähnte flexible Futter (6) in Übereinstimmung mit der Form der Vorderseite der Haut (9) vorgeformt, insbesondere geformt ist. 30
 14. Ein Verfahren nach Anspruch 13, **dadurch gekennzeichnet, dass** das erwähnte flexible Futter (6) ein geformtes Silikonfutter umfasst. 35
 15. Ein Verfahren nach einem der Ansprüche 1 bis 14, **dadurch gekennzeichnet, dass** das erwähnte flexible Futter (6) auf der Seite, gegen die die Haut (9) geformt wird, eine vorbestimmte Textur und/oder 40 Körnung, wie eine Ledertextur, aufweist.
 16. Ein Verfahren nach einem der Ansprüche 1 bis 15, **dadurch gekennzeichnet, dass** das erwähnte flexible Futter (6) eine durchschnittliche Dicke von zwischen 0,03 und 15 mm, insbesondere zwischen 0,05 und 5 mm, aufweist. 45
 17. Ein Verfahren nach einem der Ansprüche 1 bis 16, **dadurch gekennzeichnet, dass**, bevor die reaktive Polyurethanmischung auf die Oberfläche (7) des erwähnten ersten Formteils (1) aufgetragen wird, um die erwähnte Haut (9) zu formen, ein Umkehr-Coating auf diese Oberfläche (7) aufgebracht wird, insbesondere ein Lackcoating auf Wasser- oder Lösungsmittelbasis. 50
 18. Ein Verfahren nach einem der Ansprüche 1 bis 17, **dadurch gekennzeichnet, dass**, bevor die reaktive Polyurethanmischung auf die Oberfläche (7) des erwähnten ersten Formteils (1) aufgetragen wird, um die erwähnte Haut (9) zu formen, ein Einsatz (16) auf die Formoberfläche (7) gelegt wird, welche durch das flexible Futter (6) gebildet wird, wobei der Einsatz zumindest einen umgebenden Rand aufweist, durch den er anlegend an zumindest einen aufstehenden Rand (17) positioniert wird, welcher auf dem flexiblen Futter (6) vorhanden ist. 55
 19. Ein Formstück zur Verwendung in einem Verfahren nach einem der Ansprüche 1 bis 18, das zumindest ein erstes Formteil (1) aufweist, welches eine Formoberfläche (7) bildet, gegen die die erwähnte Haut (9) mit ihrer Vorderseite geformt wird, und welches zumindest zwei gegenseitig bewegliche Formabschnitte (2 - 4) umfasst, die zumindest eine Naht (5) bilden, **dadurch gekennzeichnet, dass** das erwähnte erste Formteil (1) ferner ein herausnehmbares flexibles Futter (6) aus einem elastischen Material umfasst, das optional auf der Seite, gegen die die Haut (9) geformt wird, gekörnt ist und das auf die erwähnten Formabschnitte (2 - 4) gelegt ist, um zumindest einen Abschnitt der erwähnten Formoberfläche (7) zu bilden und die erwähnte Naht (5) zumindest teilweise zu bedecken, wobei das herausnehmbare flexible Futter so konfiguriert ist, dass während des Formens in der Region oder in den Regionen, wo die Naht durch das erwähnte Futter bedeckt ist, auf der Vorderseite des geformten Artikels keine Spur der Naht sichtbar ist. 60
 20. Ein Formstück nach Anspruch 19, **dadurch gekennzeichnet, dass** die erwähnte Formoberfläche (7) eine allgemein konkave Form hat. 65
 21. Ein Formstück nach Anspruch 19 oder 20, **dadurch gekennzeichnet, dass** das erwähnte flexible Futter (6) auf der Seite, gegen die die Haut (9) geformt 70

wird, eine vorbestimmte Textur und/oder Körnung aufweist und insbesondere ein geformtes Silikonfutter umfasst.

Revendications

1. Procédé de fabrication d'un article moulé comprenant au moins une peau de polyuréthane élastomère (9) qui présente un avers et un revers, ce procédé comprenant les étapes :

- de prévision d'un moule comportant au moins une première partie de moule (1) comprenant au moins deux sections de moule mutuellement déplaçables (2-4) qui forment au moins un joint (5),
- d'application d'au moins un mélange de polyuréthane réactif sur une surface (7) de ladite première partie de moule (1) pour mouler ladite peau (9) avec son avers contre cette surface de moule (7),
- de déplacement des sections de moule mutuellement déplaçables (2-4) à l'écart l'une de l'autre, et
- d'enlèvement de l'article moulé à partir du moule,

caractérisé en ce que ladite première partie de moule (1) comprend en outre une couverture flexible (6) amovible, réalisée en une matière élastique, qui est positionnée sur lesdites sections de moule (2-4) pour former au moins une partie de ladite surface de moule (7) et pour couvrir au moins partiellement ledit joint (5), de façon que, dans la ou les régions où le joint est couvert par ladite couverture, aucune trace du joint ne soit laissée sur la surface avant de l'article moulé.

2. Procédé suivant la revendication 1, **caractérisé en ce que** ladite surface de moule (7) présente une forme généralement concave.
3. Procédé suivant l'une des revendications 1 et 2, **caractérisé en ce que** l'étape d'enlèvement de l'article moulé à partir du moule comprend l'étape d'enlèvement de l'article moulé conjointement à la couverture flexible (6) à partir des sections de moule mutuellement déplaçables (2-4) et l'étape d'enlèvement de la couverture flexible (6) à partir de l'article moulé.
4. Procédé suivant l'une quelconque des revendications 1 à 3, **caractérisé en ce que** ledit mélange réactif est pulvérisé contre ladite première partie de moule (1).
5. Procédé suivant l'une quelconque des revendica-

tions 1 à 3, **caractérisé en ce que** ledit moule comprend au moins une seconde partie de moule (11) coopérant avec la première partie de moule (1) pour former une cavité de moule fermée dans laquelle ledit mélange de polyuréthane réactif est appliqué, en particulier conformément à un processus de réaction et moulage par injection (RMI), ladite seconde partie de moule (11) étant en particulier composée de seulement une section de moule.

6. Procédé suivant la revendication 5, **caractérisé en ce que** ledit mélange de polyuréthane réactif comprend un agent gonflant et **en ce qu'il** est formulé pour produire une mousse de polyuréthane présentant ladite peau (9) sous la forme d'une peau intégrale moulée contre cette surface de moule (7).

7. Procédé suivant l'une quelconque des revendications 1 à 5, **caractérisé en ce que** ledit mélange de polyuréthane réactif est formulé pour produire une peau de polyuréthane élastomère (9) non cellulaire ou microcellulaire ayant une densité supérieure à 400 kg/m³, et de préférence supérieure à 700 kg/m³.

8. Procédé suivant l'une quelconque des revendications 1 à 7, **caractérisé en ce que**, avant déplacement des sections de moule mutuellement déplaçables (2-4) à l'écart l'une de l'autre pour enlever l'article moulé à partir du moule, au moins une première couche de renfort (12) est moulée contre le revers de la peau moulée (9).

9. Procédé suivant la revendication 8, **caractérisé en ce que** l'étape de moulage de ladite première couche de renfort (12) comprend une application d'une composition moussable pour obtenir une matière mousse contre le revers de la peau moulée (9).




10. Procédé suivant la revendication 9, **caractérisé en ce que** ladite composition moussable est appliquée entre la peau moulée (9) et une seconde couche de renfort structurelle (10) qui est positionnée sur le côté revers de la peau (9), la matière mousse obtenue par la composition moussable réunissant la couche de renfort structurelle (10) au revers de la peau moulée (9).

11. Procédé suivant la revendication 9, **caractérisé en ce que**, avant déplacement des sections de moule mutuellement déplaçables (2-4) à l'écart l'une de l'autre pour enlever l'article moulé à partir du moule, une seconde couche de renfort structurelle (10) est moulée contre le revers de la couche de mousse (12).



12. Procédé suivant la revendication 8, **caractérisé en ce que** la première couche de renfort est une cou-

- che de renfort structurelle (10) réalisée en une matière rigide.
13. Procédé suivant l'une quelconque des revendications 1 à 12, **caractérisé en ce que** ladite couverture flexible (6) est préformée, en particulier moulée, conformément à la forme de l'avant de la peau (9). 5
14. Procédé suivant la revendication 13, **caractérisé en ce que** ladite couverture flexible (6) comprend une couverture de silicone moulée. 10
15. Procédé suivant l'une quelconque des revendications 1 à 14, **caractérisé en ce que** ladite couverture flexible (6) présente, sur sa face contre laquelle la peau (9) est moulée, une texture et/ou grain prédéterminés, comme une texture de cuir. 15
16. Procédé suivant l'une quelconque des revendications 1 à 15, **caractérisé en ce que** ladite couverture flexible (6) présente une épaisseur moyenne comprise entre 0,03 et 15 mm, en particulier entre 0,05 et 5 mm. 20
17. Procédé suivant l'une quelconque des revendications 1 à 16, **caractérisé en ce que**, avant d'appliquer le mélange de polyuréthane réactif sur la surface (7) de ladite première partie de moule (1) pour mouler ladite peau (9), un revêtement dans le moule est appliqué sur cette surface (7), en particulier un revêtement de peinture à base d'eau ou de solvant. 25
18. Procédé suivant l'une quelconque des revendications 1 à 17, **caractérisé en ce que**, avant d'appliquer le mélange de polyuréthane réactif à la surface (7) de ladite première partie de moule (1) pour mouler ladite peau (9), un insert (16) est positionné sur la surface du moule (7) formée par la couverture flexible (6), l'insert présentant au moins un bord périphérique au moyen duquel il est positionné en appui sur au moins un bord en saillie (17) prévu sur la couverture flexible (6). 30
19. Moule à mettre en oeuvre dans un procédé suivant l'une quelconque des revendications 1 à 18, et présentant au moins une première partie de moule (1) qui forme une surface de moule (7) contre laquelle ladite peau (9) est moulée par son avers et qui comprend au moins deux sections de moule mutuellement déplaçables (2-4) formant au moins un joint (5), **caractérisé en ce que** ladite première partie de moule (1) comprend en outre une couverture flexible (6) amovible réalisée en une matière élastique qui est éventuellement grenue sur sa face contre laquelle la peau (9) est moulée et qui est positionnée sur lesdites sections de moule (2-4) pour former au moins une partie de cette surface de moule (7) et pour couvrir partiellement au moins ledit joint (5), la couverture flexible amovible étant configurée de façon que, pendant le moulage, dans la ou les régions où le joint est couvert par ladite couverture, aucune trace du joint ne soit laissée sur la surface avant de l'article moulé. 35
20. Moule suivant la revendication 19, **caractérisé en ce que** ladite surface de moule (7) a une forme généralement concave. 40
21. Moule suivant l'une des revendications 19 et 20, **caractérisé en ce que** ladite couverture flexible (6) montre une texture et/ou grain prédéterminés sur sa face contre laquelle la peau (9) est moulée et **en ce qu'elle** comprend en particulier une couverture de silicone moulée. 45



EP 1 320 451 B1



EP 1 320 451 B1



EP 1 320 451 B1



EP 1 320 451 B1




Fig. 8




Fig. 9




Fig. 10

EP 1 320 451 B1




Fig. 11